

(Adopted November 4, 1988)(Amended May 5, 1989)(Amended June 2, 1989)
(Amended March 2, 1990)(Amended November 2, 1990)(Amended December 7, 1990)
(Amended August 2, 1991)(Amended January 13, 1995)
(Proposed Amended Rule 1106 September 2015)

PROPOSED AMENDED RULE 1106.

MARINE AND PLEASURE CRAFT
COATING OPERATIONS

(a) Purpose

The purpose of this rule is to reduce emissions of volatile organic compounds (VOC) and stratospheric ozone depleting and global warming compounds from Marine and Pleasure Craft Coating Operations.

(ab) Applicability

This rule applies to:

(1) MARINE COATING OPERATIONS:

~~This rule applies to~~Which means all coating operations of boats, ships, and vessels, and their appurtenances, including but not limited to structures, such as piers, docks~~and, to~~buoys and oil drilling rigs, intended for the exposure to either a marine or fresh water environment.~~Coating operations of vessels which are manufactured or operated primarily for recreational purposes are subject to the requirements of Rule 1106.1-- Pleasure Craft Coating Operations.~~

(2) PLEASURE CRAFT COATING OPERATIONS:

Which means all coating operations for purposes of refinishing, repairing, modifying, or manufacturing of pleasure craft as defined in paragraph (c)(29) of this rule, and to their parts and components.

(bc) Definitions

For the purpose of this rule the following definitions shall apply:

- (1) AEROSOL COATING PRODUCT ~~is~~means a pressurized coating product containing pigments, ~~or~~resins, and/or other coating solids that ~~is dispensed~~dispenses product ingredients by means of a propellant, and is packaged in a disposable aerosol container~~can~~ for hand-held application, or for use in specialized equipment for ground marking and traffic~~marking applications.~~
- (2) AIR DRIED COATING is any coating that is formulated by the manufacturer to be cured at a temperature below 90 ~~°C~~ (194 ~~°F~~).

- (3) ANTENNA COATING is any coating applied to equipment and associated structural appurtenances which are used to receive or transmit electromagnetic signals.
- (4) ~~ANTIFOULING~~ ANTIFOULANT COATING is any coating applied to the underwater portion of ~~a boats, ships, vessels, vessel or pleasure craft~~ to prevent or reduce the attachment of biological organisms. ~~An antifouling coating and~~ shall be registered with the ~~Environmental Protection Agency (EPA) as a pesticide~~ United States Environmental Protection Agency ("U.S. EPA") as a pesticide under the Federal Insecticide, Fungicide, and Rodenticide Act (7 United States Code Section 136).
- (5) BAKED COATING is any coating that is formulated by the manufacturer to be cured at a temperature at or above 90 °C (194 °F).
- (6) CLEAR WOOD COATINGS are clear and semi-transparent topcoats applied to wood substrates to provide a transparent or translucent film.
- (7) DISTRIBUTOR means any person to whom a consumer product is sold or supplied for the purposes of resale or distribution in commerce, except that manufacturers, retailers, and consumers are not distributors.
- ~~(68)~~ ELASTOMERIC ADHESIVE is any adhesive containing natural or synthetic rubber.
- ~~(79)~~ EXEMPT COMPOUNDS ~~are any of the following compounds:~~ (See Rule 102 - Definition of Terms).
- ~~— (A) Group I (General)~~
- ~~— trifluoromethane (HFC-23)~~
- ~~— pentafluoroethane (HFC-125)~~
- ~~— 1,1,2,2-tetrafluoroethane (HFC-134)~~
- ~~— tetrafluoroethane (HFC-134a)~~
- ~~— 1,1,1-trifluoroethane (HFC-143a)~~
- ~~— 1,1-difluoroethane (HFC-152a)~~
- ~~— chlorodifluoromethane (HCFC-22)~~
- ~~— dichlorotrifluoroethane (HCFC-123)~~
- ~~— 2-chloro-1,1,1,2-tetrafluoroethane (HCFC-124)~~
- ~~— dichlorofluoroethane (HCFC-141b)~~
- ~~— chlorodifluoroethane (HCFC-142b)~~
- ~~— cyclic, branched, or linear, completely fluorinated alkanes~~
- ~~— cyclic, branched, or linear, completely fluorinated ethers with no unsaturations~~

- ~~—cyclic, branched, or linear, completely fluorinated tertiary amines with no unsaturations~~
- ~~—sulfur-containing perfluorocarbons with no unsaturations and with sulfur bonds only to carbon and fluorine~~
- ~~—(B) Group II~~
 - ~~—methylene chloride~~
 - ~~—1,1,1-trichloroethane (methyl chloroform)~~
 - ~~—trichlorotrifluoroethane (CFC-113)~~
 - ~~—dichlorodifluoromethane (CFC-12)~~
 - ~~—trichlorofluoromethane (CFC-11)~~
 - ~~—dichlorotetrafluoroethane (CFC-114)~~
 - ~~—chloropentafluoroethane (CFC-115)~~

~~The use of Group II compounds and/or carbon tetrachloride may be restricted in the future because they are toxic, potentially toxic, upper-atmosphere ozone depleters, or cause other environmental impacts. By January 1, 1996, production of chlorofluorocarbons (CFC), 1,1,1-trichloroethane (methyl chloroform), and carbon tetrachloride will be phased out in accordance with the Code of Federal Regulation Title 40, Part 82 (December 10, 1993).~~

- (810) EXTREME HIGH GLOSS COATING is any coating which achieves at least 95 percent reflectance on a 60° meter when tested by ASTM Method D-523-14, the Standard Test Method for Specular Gloss.
- (11) FINISH PRIMER/SURFACER is any coating applied with a wet film thickness of less than 10 mils (one mil = 0.001 of an inch) and is applied prior to the application of a Marine or Pleasure Craft Coating for the purpose of providing corrosion resistance, adhesion for subsequent coatings, a moisture barrier, and promotes a uniform surface necessary for filling in surface imperfections.
- (912) GRAMS OF VOC PER LITER OF COATING, LESS WATER AND LESS EXEMPT COMPOUNDS, OR REGULATORY VOC, is the weight of VOC per combined volume of VOC and coating solids and can be calculated by the following equation:

Grams of VOC per Liter of Coating,

$$\text{Less Water and Less Exempt Compounds} = \frac{W_s - W_w - W_{es}}{V_m - V_w - V_{es}}$$

Where: W_s = weight of volatile compounds in grams
 W_w = weight of water in grams
 W_{es} = weight of exempt compounds in grams
 V_m = volume of material in liters
 V_w = volume of water in liters
 V_{es} = volume of exempt compounds in liters

(13) GRAMS OF VOC PER LITER OF MATERIAL, OR ACTUAL VOC, is the weight of VOC per volume of material and shall be calculated by the following equation:

$$\text{Grams of VOC per Liter of Material} = \frac{W_s - W_w - W_{es}}{V_m}$$

Where: W_s = weight of volatile compounds in grams
 W_w = weight of water in grams
 W_{es} = weight of exempt compounds in grams
 V_m = volume of material in liters

- ~~(14)~~ HEAT RESISTANT COATING is any coating which during normal use must withstand temperatures of at least 204 °C (400 °F).
- ~~(15)~~ HIGH GLOSS COATING is any coating which achieves at least 85 percent reflectance on a 60° meter when tested by ASTM Method D-523-14, the Standard Test Method for Specular Gloss.
- ~~(16)~~ HIGH TEMPERATURE COATING is any coating that during normal use ~~which~~ must withstand temperatures of at least 426 °C (800 °F).
- (17) HIGH BUILD PRIMER/SURFACER is any coating applied with a wet film thickness of 10 mils or more (one mil = 0.001 of an inch) prior to the application of a topcoat for purposes of providing corrosion resistance, adhesion of subsequent coatings, a moisture barrier, or promoting a uniform surface necessary for filling in surface imperfections.
- (18) HIGH-VOLUME, LOW-PRESSURE (HVLP) means spray application equipment designed to atomize 100 percent by air pressure only and is operated between 0.1 and 10 pounds per square inch gauge (psig), air atomizing pressure measured dynamically at the center of the air cap and at the air horns.
- (19) INORGANIC ZINC COATING is a coating that contains 960 grams per liter or more elemental zinc incorporated into an inorganic silicate binder that is applied to steel to provide galvanic corrosion resistance.

- (~~13~~20) LOW ACTIVATION INTERIOR COATING is any coating used on interior surfaces aboard ~~ships-boats, ships, and vessels,~~ to minimize the activation of pigments on painted surfaces within a radiation environment.
- (21) LOW-SOLIDS COATINGS are coatings containing one pound or less of solids per gallon of material.
- (~~14~~22) MARINE COATING is any coating, except unsaturated polyester resin (fiberglass) coatings, containing volatile organic materials and applied by any means to ~~ships,-~~boats, ships, and vessels, and their appurtenances, structures such as piers and docks intended for exposure to a marine environment, and also to buoys and oil drilling rigs intended for the marine environment.
- (23) MARINE DECK SEALANT PRIMER is any sealant primer intended by the manufacturer to be applied to wooden marine decks. A sealant primer is any product intended by the manufacturer to be applied to a substrate, prior to the application of a sealant, to enhance the bonding surface.
- (~~15~~24) METALLIC HEAT RESISTANT COATING is any coating which contains more than 5 grams of metal particles per liter of coating as applied and which must withstand temperatures over 80 °C (~~175~~176 °F).
- (25) MIST COATING is any low viscosity, thin film, epoxy coating applied to an inorganic zinc primer that penetrates the porous zinc primer and allows the occluded air to escape through the film prior to curing.
- (~~16~~26) NAVIGATIONAL AIDS COATING is any coating that is applied to ~~are~~ buoys or other Coast Guard waterway markers that are recoated aboard ship at their usage site and immediately returned to the water.
- (27) NONSKID COATING means any coating applied to the horizontal surface of a marine vessel for the specific purpose of providing slip resistance for personnel.
- (28) ORGANIC ZINC COATING is a coating that contains 960 grams per liter or more elemental zinc incorporated into an organic silicate binder that is applied to steel to provide galvanic corrosion resistance.
- (~~17~~) ~~PRETREATMENT WASH PRIMER~~ is any coating which contains at least 1/2-percent acids, by weight, to provide surface etching and is applied directly to metal surfaces to provide corrosion resistance, adhesion, and ease of stripping.

- (29) PLEASURE CRAFT are marine or fresh water vessels that are less than 20 meters in length and are manufactured or operated primarily for recreational purposes, or are leased, rented, or chartered to a person or business for recreational purposes. Amusement theme parks that operate vessels in a fresh water environment solely for the purpose of an amusement park attraction shall be considered pleasure craft vessels regardless of their length. The owner or operator of a pleasure craft vessel shall be responsible for certifying that the intended use is for recreational purposes.
- (30) PLEASURE CRAFT COATING is any marine coating, except unsaturated polyester resin (fiberglass) coatings, applied by brush, spray, roller, or other means to a pleasure craft. A pleasure craft coating that is sold, offered for sale, or solicited for use within the South Coast Air Quality Management District (SCAQMD) jurisdiction must be designated by the manufacturer as a pleasure craft coating by any sticker or label affixed on the container, or where it is indicated in any sales or advertising literature, that the coating may be used as, or is suitable for use as, a pleasure craft coating.
- (31) PRETREATMENT WASH PRIMER is a coating which contains a minimum of 1/2 percent acid, by weight, applied directly to bare metal surfaces to provide necessary surface etching.
- ~~(1832)~~ REPAIR AND MAINTENANCE THERMOPLASTIC COATING is any resin-bearing coating, such as vinyl, chlorinated rubber, or bituminous coatings, in which the resin becomes pliable with the application of heat, and is used to recoat portions of a previously coated substrate which has sustained damage to the coating following normal coating operations.
- ~~(1933)~~ SEALANT FOR WIRE-SPRAYED ALUMINUM is any coating of up to one mil (one mil = 0.001 of an inch) in thickness of an epoxy material which is reduced for application with an equal part of an appropriate solvent (naphtha, or ethylene glycol monoethyl ether).
- (34) SEALER is a coating applied to bare wood to seal surface pores to prevent subsequent coatings from being absorbed into the wood.
- ~~(2035)~~ SOLVENT CLEANING OPERATION is ~~the removal of loosely held uncured adhesives, uncured inks, uncured coatings, and contaminants from parts, products, tools, machinery, equipment, and general work areas. Contaminants include, but are not limited to, dirt, soil, and grease. In a~~

~~cleaning process which consists of a series of cleaning methods, each distinct method shall constitute a separate solvent cleaning operation~~ as defined in Rule 1171 - Solvent Cleaning Operations.

- (~~21~~36) SPECIAL MARKING COATING is any coating used for items such as flight decks, ~~ships'~~ vessel identification numbers, and other demarcations for safety ~~/or~~ identification applications.
- (~~22~~37) TACK COAT is an epoxy coating of up to two mils (~~0.002 inch~~) (one mil = 0.001 of an inch) thick applied to an existing epoxy coating. The existing epoxy coating must have aged beyond the time limit specified by the manufacturer for application of the next coat.
- (38) TEAK PRIMER is a coating applied to teak wood or previously oiled teak wood decks in order to improve the adhesion of a seam sealer.
- (39) TOPCOAT is any final coating applied to the interior or exterior of a marine or pleasure craft.
- (~~23~~40) TOUCH-UP COATING is any coating operation incidental to the main coating process but necessary ~~used~~ to cover minor imperfections ~~prior to shipment appearing after the main coating operation~~ or minor mechanical damage incurred prior to intended use.
- (41) TRANSFER EFFICIENCY means the amount of coating solids adhering to the object being coated divided by the total amount of coating solids sprayed; expressed as a percentage.
- (~~24~~42) UNDERSEA WEAPONS SYSTEM COATING is any coating applied to any or all components of a weapons system intended for exposure to a marine environment and that is intended to be launched or fired ~~underwater~~ undersea.
- (43) VARNISHES are clear or pigmented wood topcoats formulated with various resins to dry by chemical reaction.
- (~~25~~44) VOLATILE ORGANIC COMPOUND (VOC) is ~~any volatile compound of carbon, excluding methane, carbon monoxide, carbon dioxide, carbonic acid, metallic carbides or carbonates, ammonium carbonate, and exempt compounds~~ as defined in Rule 102 - Definition of Terms.
- (~~26~~45) WIRE-SPRAYED ALUMINUM is any molten multi-aluminum coating applied to a steel substrate using oxygen fueled combustion spray ~~methods~~ equipment.

(ed) Requirements

(1) VOC Content of Marine Coatings

Except as otherwise provided in this rule, a person shall not apply a marine coating within the SCAQMD jurisdiction with a VOC content in excess of the following limits shown in the Table of Standards I, expressed as grams of VOC per liter of coating, as applied, less water and less exempt solvents:

	Baked	Air Dried
General Coating	275 g/L	340 g/L
Specialty Coating		
Heat Resistant	360	420
Metallic Heat Resistant		530
High Temperature		500
Pre-Treatment Wash Primer	780	780
Underwater		
Weapons Systems	275	340
Elastomeric Adhesives with 15%, by Weight, Natural or Synthetic Rubber		730
Solvent-Based Inorganic Zinc		650
Navigational Aids		340
Sealant for Wire Sprayed Aluminum		610
Special Marking		490
Tack Coat		610
Low Activation Interior Coating		420
Repair and Maintenance Thermoplastic		550
Extreme High-Gloss Coating	420	490
Antenna Coating		530
Antifoulant		400
High Gloss	275	340

TABLE OF STANDARDS I

<u>MARINE COATING</u>	<u>VOC LIMITS</u> <u>Less water and exempt compounds</u>
-----------------------	---

<u>CATEGORY</u>	<u>Grams per Liter (g/L)</u>	
	<u>BAKED</u> <u>CURRENT LIMIT</u>	<u>AIR DRIED</u> <u>CURRENT LIMIT</u>
<u>Antenna Coating</u>		<u>340</u>
<u>Antifoulant Coatings:</u>		
<u>Aluminum Substrates</u>		<u>560</u>
<u>Other Substrates</u>		<u>400</u>
<u>Elastomeric Adhesives (with 15%, by Weight, Natural or Synthetic Rubber)</u>		<u>730</u>
<u>Inorganic Zinc Coating</u>		<u>340</u>
<u>Low Activation Interior Coating</u>		<u>420</u>
<u>Mist Coating</u>		<u>610</u>
<u>Navigational Aids Coating</u>		<u>340</u>
<u>Nonskid Coating</u>		<u>340</u>
<u>Organic Zinc Coating</u>		<u>340</u>
<u>Pre-Treatment Wash Primer</u>	<u>420</u>	<u>420</u>
<u>Repair and Maintenance Thermoplastic Coating</u>		<u>340</u>
<u>Sealant for Wire-Sprayed Aluminum</u>		<u>610</u>
<u>Special Marking Coating</u>		<u>420</u>
<u>Specialty Coatings:</u>		
<u>Heat Resistant Coating</u>	<u>360</u>	<u>420</u>
<u>Metallic Heat Resistant Coating</u>		<u>530</u>
<u>High Temperature Coating</u>		<u>500</u>
<u>Tack Coating</u>		<u>610</u>
<u>Topcoats:</u>		
<u>Extreme High-Gloss Coating</u>	<u>420</u>	<u>490</u>
<u>High Gloss Coating</u>	<u>275</u>	<u>340</u>
<u>Underwater Weapons Systems Coating</u>	<u>275</u>	<u>340</u>
<u>Any Other Coating Type</u>	<u>275</u>	<u>340</u>

(2) VOC Content of Pleasure Craft Coatings

Except as otherwise provided in this rule, a person shall not apply a pleasure craft coating within the SCAQMD jurisdiction with a VOC content in excess of the following limits shown in the Table of Standards II, expressed as grams of VOC per liter of coating, as applied, less water and less exempt solvents:

TABLE OF STANDARDS II

<u>VOC LIMITS</u> <u>Less water and exempt compounds</u> <u>Grams per Liter (g/L)</u>	
<u>PLEASURE CRAFT</u>	<u>CURRENT LIMIT</u>

<u>COATING CATEGORY</u>	
<u>Antifoulant Coatings:</u>	
<u>Aluminum Substrate</u>	<u>560</u>
<u>Other Substrate</u>	<u>330</u>
<u>Clear Wood Coatings:</u>	
<u>Sealers</u>	<u>550</u>
<u>Varnishes</u>	<u>490</u>
<u>Primer Coatings:</u>	
<u>Finish Primer/Surfacer</u>	<u>420</u>
<u>High Build Primer/Surfacer</u>	<u>340</u>
<u>Marine Deck Sealant Primer</u>	<u>760</u>
<u>Pretreatment Wash Primer</u>	<u>780</u>
<u>Teak Primer</u>	<u>775</u>
<u>Topcoats:</u>	
<u>Extreme High Gloss Coating</u>	<u>490</u>
<u>High Gloss Coating</u>	<u>420</u>
<u>Any Other Coating Type</u>	<u>420</u>

(3) VOC Content of Low-Solids Coatings

Except as otherwise provided in this rule, a person shall not apply a marine coating or a pleasure craft coating within the SCAQMD jurisdiction with a VOC content in excess of the following limit shown in the Table of Standards III, expressed as grams of VOC per material of coating, as applied:

TABLE OF STANDARDS III

<u>VOC LIMIT – MARINE & PLEASURE CRAFT COATINGS</u> <u>Grams per liter of material VOC</u>	
<u>COATING CATEGORY</u>	<u>CURRENT LIMIT</u>
<u>Low-Solids Coating</u>	<u>120</u>

(4) Most Restrictive VOC Limit

If any representation or information on the container of any coating subject to this rule, or any label or sticker affixed to the container, or in any sales, advertising, or technical literature that indicates that the coating meets the definition of or is recommended for use for more than one of the marine coating categories listed in subparagraph (d)(1) or the pleasure craft coating categories listed in subparagraph (d)(2), or the low-solids

coating category listed in subparagraph (d)(3), then the lowest VOC content limit shall apply.

~~anywhere on the container of any coating listed in either Table of Standards or label therefor literature~~ any representation is made that the coating may be used as, or is suitable for use as, a for which a lower standard is specified in the table or in paragraph (d)(1) or (d)(2), standard

(25) Approved Emission Control System

(A) ~~Approved Emission Control System~~

~~Owners and/or operators may comply with the provisions of paragraph (e)(1) by using an emission control system, which has been approved in writing by the Executive Officer, for reducing VOC emissions. The control system must achieve a minimum capture efficiency using USEPA, ARB, and District methods specified in subparagraph (e)(4)(A) and a destruction efficiency of at least 85 percent by weight, and,~~

~~(B) The approved system shall reduce the VOC emissions, when using non-compliant coatings, to an equivalent or greater level that would be achieved by the provisions in paragraph (e)(1)~~ A person may comply with the provisions of paragraphs (d)(1), (d)(2) or (d)(3), by using an approved emission control system, consisting of a collection and control device, provided such emission control system is approved pursuant to Rule 203 - Permit to Operate, in writing, by the Executive Officer for reducing emissions of VOC. The Executive Officer shall approve such emission control system only if the VOC emissions resulting from the use of non-compliant coatings will be reduced to a level equivalent to or lower than the limits specified in paragraphs (d)(1), (d)(2) or (d)(3), as applicable.
The required efficiency of an emission control system at which an equivalent or greater level of VOC reduction will be achieved shall be calculated by the following equation:

$$C.E. = \left[1 - \left\{ \frac{(VOC_{LWc})}{(VOC_{LWn,Max})} \times \frac{1 - (VOC_{LWn,Max}/D_{n,Max})}{1 - (VOC_{LWc}/D_c)} \right\} \right] \times 100\%$$

Where: C.E. = Control Efficiency, expressed as a percentage

VOC_{LWc}	=	VOC Limit of Rule 1106, less water and less exempt compounds, pursuant to subdivision (c).
$VOC_{LWn,Max}$	=	Maximum VOC content of non-compliant coating used in conjunction with a control device, less water and less exempt compounds.
$D_{n,Max}$	=	Density of solvent, reducer, or thinner contained in the non-compliant coating, containing the maximum VOC content of the multi-component coating.
D_c	=	Density of corresponding solvent, reducer, or thinner used in the compliant coating system = 880 g/L.

(36) Alternative Emission Control Plan

~~Owners and/or operators may achieve compliance with the requirements~~ A person may comply with the provisions of paragraphs (d)(1), (d)(2) and (d)(3) ~~paragraph (e)(1)~~ by means of an Alternative Emission Control Plan, pursuant to Rule 108 - Alternative Emissions Control Plans.

(7) Exempt Compounds

A person shall not manufacture, sell, offer for sale, distribute for use in the SCAQMD jurisdiction, or apply any marine or pleasure craft coating which contains any Group II Exempt Compounds listed in Rule 102 - Definition of Terms, in quantities greater than 0.1 percent by weight. Cyclic, branched, or linear, completely methylated siloxanes (VMS) are not subject to this provision.

(8) Carcinogenic Materials

A person shall not manufacture, sell, offer for sale, distribute for use in the SCAQMD jurisdiction, or apply any marine or pleasure craft coating which contains cadmium, nickel, lead or hexavalent chromium was introduced as a pigment or as an agent to impart any property or characteristic to the marine or pleasure craft coatings during manufacturing, distribution, or use of the applicable marine or pleasure craft coatings.

(9) Transfer Efficiency

(A) Effective April 1st, 2016 a person shall not apply any marine coating or pleasure craft coating unless one of the following methods of coating transfer is used:

(i) electrostatic application, or

(ii) high-volume, low-pressure (HVLP) spray, or

(iii) brush, dip, or roller, or

(iv) Spray gun application, provided the owner or operator demonstrates that the spray gun meets the HVLP definition in paragraph (c)(18) in design and use. A satisfactory demonstration must be based on the manufacturer's published technical material on the design of the spray gun and by a demonstration of the operation of the spray gun using an air pressure tip gauge from the manufacturer of the spray gun.

(v) Any such other marine coating or pleasure craft coating application methods as demonstrated, in accordance with the provisions of paragraph (h)(4), to be capable of achieving equivalent or better transfer efficiency than the marine coating or pleasure craft coating application method listed in clause (d)(9)(A)(ii), provided written approval is obtained from the Executive Officer prior to use.

(B) A person shall not apply any marine coating or pleasure craft coating by any of the methods listed in subparagraph (d)(9)(A) unless such coating is applied with properly operating equipment, operated according to procedures recommended by the manufacturer and in compliance with applicable permit conditions, if any.

~~(410)~~ Solvent Cleaning ~~Operations~~; Storage and Disposal of VOC-containing Materials

~~All solvent~~ Solvent cleaning ~~operations~~ of application equipment, parts, products, tools, machinery, equipment, general work areas, and the storage and disposal of VOC-containing materials used in solvent cleaning operations shall be carried out pursuant to SCAQMD Rule 1171 - Solvent Cleaning Operations.

~~(5) — Recordkeep Notwithstanding the provisions of subdivision (g), records shall be maintained pursuant to Rule 109.~~

~~(d) — Prohibition of Specification~~

~~(1) — A person shall not solicit or require any other person to use, in the district, any coating or combination of coatings to be applied to any marine vessel or marine component subject to the provisions of this rule that does not meet the limits requirements of this rule or of an Alternative Emission Control Plan approved pursuant to the provisions of paragraph (e)(3) of this rule.~~

~~(2) — The requirements of paragraph (d)(1) shall apply to all written or oral agreements executed or entered into after November 4, 1988.~~

(e) Prohibition of Possession, Specification and Sale

(1) For the purpose of this rule, no person shall supply, sell, offer for sale, market, manufacture, blend, repackage, apply, store at a worksite, or solicit the application of any marine coating or pleasure craft coating within the SCAQMD jurisdiction that is not in compliance with the requirements shown in the Table of Standards of paragraphs (d)(1), (d)(2), and (d)(3) unless one or more of the following conditions apply:

(A) The marine or pleasure craft coating is for use at a facility that utilizes an approved emission control device pursuant to subparagraph (d)(5) and the coating meets the limits specified in permit conditions.

(B) The marine or pleasure craft coating is for use at a facility that operates in compliance with an approved Alternative Emissions Control Plan pursuant to subparagraph (d)(6), and the marine or pleasure craft coating is specified in the plan.

(C) The requirements of paragraphs (d)(7) and (d)(8).

(2) For the purpose of this rule, no person shall solicit from, specify, or require any other person to use in the SCAQMD jurisdiction any marine or pleasure craft coating which, does not meet the:

(A) Applicable VOC limits required by paragraph (d)(1), (d)(2) or (d)(3) for the specific application unless:

(i) The marine or pleasure craft coating is located at a facility that utilizes an approved emission control device pursuant

- to paragraph (d)(5), and the marine or pleasure craft coating meets the limits specified in permit conditions; or,
- (ii) The marine or pleasure craft coating is located at a facility that operates in compliance with an approved Alternative Emissions Control Plan pursuant to paragraph (d)(6), and the marine or pleasure craft coating is specified in the plan.
- (B) The requirements of paragraphs (d)(7) and (d)(8).
- (3) For the purpose of this rule, no person shall supply, sell, offer for sale, market, blend, package, repackage or distribute any marine or pleasure craft coating for use within the SCAQMD jurisdiction subject to the provisions in this rule which, does not meet the:
- (A) Applicable VOC limits required by paragraphs (d)(1), (d)(2) and (d)(3) for the specific application, unless:
- (i) The marine or pleasure craft coating is for use at a facility that utilizes an approved emission control device pursuant to paragraph (d)(5), and the coating meets the limits specified in permit conditions; or,
- (ii) The marine or pleasure craft coating is for use at a facility that operates in accordance with an approved Alternative Emissions Control Plan pursuant to paragraph (d)(6), and the marine or pleasure craft coating is specified in the plan; and,
- (iii) The person that supplies, sells, offers for sale, markets, blends, packages, repackages or distributes the marine or pleasure craft coating keeps the following records for at least five years and makes them available to the Executive Officer upon request:
- (I) Marine or pleasure craft coating name and manufacturer;
- (II) VOC content of the marine or pleasure craft coating;
- (III) Documentation such as manufacturer specification sheets, material safety data sheets, technical data sheets, or any other air quality data sheets that

demonstrate that the material is intended for use as a marine or pleasure craft coating;

(B) The requirements of paragraphs (d)(7) and (d)(8).

(4) For the purpose of this rule, no person shall solicit from, specify, require, offer for sale, sell, or distribute to any other person for use in the SCAQMD jurisdiction any marine or pleasure craft coating application equipment which does not meet the requirements of subparagraph (d)(9)(A).

(5) For the purpose of this rule, no person shall offer for sale, sell, supply, market, offer for sale or distribute an HVLP spray gun for use within the SCAQMD unless the person offering for sale, selling, marketing or distributing the HVLP spray gun for use within the SCAQMD provides accurate information to the spray gun recipient on the maximum inlet air pressure to the spray gun which would result in a maximum air pressure of 10 pounds per square inch gauge (psig) air pressure measured dynamically at the center of the air cap and at the air horns based on the manufacturer's published technical material on the design of the spray application equipment and by a demonstration of the operation of the spray application equipment using an air pressure tip gauge from the manufacturer of the gun. The information shall either be permanently marked on the gun, or provided on the company's letterhead or in the form of technical literature which clearly identifies the spray gun manufacturer, the seller, or the distributor.

(6) Paragraphs (d)(1), (d)(2) and (d)(3) shall not apply to marine coatings or pleasure craft coatings that are sold, offered for sale, or solicited, for shipment or use outside of the SCAQMD jurisdiction, or for shipment to other manufacturers for repackaging provided such coatings are sold, offered for sale, or solicited, for shipment or use outside the SCAQMD jurisdiction.

(f) Recordkeeping Requirements

(1) Recordkeeping for VOC Emissions

Records of marine coating usage and pleasure craft coating usage, as applicable, shall be maintained pursuant to SCAQMD Rule 109 - Recordkeeping for Volatile Organic Compound Emissions, and shall be

made available to the Executive Officer upon request. The records shall also include the following information:

- (A) Material name and manufacturer;
- (B) Application method;
- (C) Marine coating and pleasure craft coating categories, as applicable, and mix ratio specific to the coating;
- (D) Regulatory VOC, for the marine coating and pleasure craft coating, as applicable;
- (E) Documentation such as manufacturer specification sheets, material safety data sheets, technical data sheets, or any other air quality data sheets that indicate the material is intended for use as a marine coating, pleasure craft coating or solvent, as applicable;
- (F) Current manufacturer specification sheets, material safety data sheets, or technical data sheets, which list the actual VOC and regulatory VOC, for each marine and pleasure craft coating, as applicable; and,

(2) Recordkeeping Requirements for Emission Control System

Any person using an emission control system shall maintain daily records of key system operating parameters which will demonstrate continuous operation and compliance of the emission control system during periods of VOC emission producing activities. "Key system operating parameters" are those parameters necessary to ensure or document compliance with subparagraph (h)(5)(A), including, but not limited to, temperatures, pressure drops, and air flow rates. These records shall be made available to the Executive Officer upon request.

(g) Administrative Requirements for Marine Coating Manufacturers

(1) Compliance Statement Requirement

Effective April 1st, 2016 for each individual marine coating and pleasure craft coating, marine coating and pleasure craft coating component, and ready to spray mixtures (based on the manufacturers stated mix ratio) sold, offered for sale, for shipment or use within the SCAQMD jurisdiction, the manufacturer shall include the following information on a product data sheet, or an equivalent medium:

- (A) The actual VOC and regulatory VOC for marine coating and pleasure craft coating, as applicable; and

(B) The weight percentage of volatiles, water, and exempt compounds; and,

(C) The density of the material (in grams per liter).

(2) Labeling Requirements

(A) The manufacturer of marine coatings and pleasure craft coatings or marine coating and pleasure craft coating components shall include on all containers the regulatory VOC content, as supplied (in grams of VOC per liter of coating less water and exempt compounds).

(3) Reporting Requirements

(A) Annual Quantity Emissions Reports (AQER)

Effective April 1st, 2016 and thereafter, for each calendar year (January 1 through December 31) beginning with 2015 and continuing with each subsequent calendar year until 2018, a marine coating or pleasure craft coating manufacturer or distributor shall submit to the SCAQMD by April 1st of the following calendar year, an annual quantity and emissions report for products subject to the rule that were sold or distributed for sale within the SCAQMD jurisdiction. The report format shall be approved by the Executive Officer, and shall include the annual sales or distribution volume and the regulatory VOC content of marine coatings and pleasure craft coatings sold or distributed within the SCAQMD jurisdiction.

(B) List of Distributors

Effective April 1st, 2016 and thereafter, for each calendar year (January 1 through December 31) beginning with 2015 and continuing with each subsequent calendar year until 2018, each manufacturer or distributor of a marine coating or pleasure craft coating that were sold or distributed for sale within the SCAQMD jurisdiction, shall submit to the SCAQMD by April 1st a list of all U.S. distributors to whom they supply products that are subject to this rule, including but not limited to, private label marine coating or pleasure craft coatings, and toll manufactured marine coatings or pleasure craft coatings. The report format shall be approved by

the Executive Officer and shall include the distributor's name, address, contact person and telephone number.

(eh) Test Methods

(1) Determination of VOC Content:

The VOC content of coatings, subject to the provisions of this rule shall be determined by the following methods:

- (A) ~~United States Environmental Protection Agency (U.S. EPA)~~ Reference Test Method 24 (Determination of Volatile Matter Content, Water Content, Volume Solids and Weight Solids of Surface Coatings, Code of Federal Regulations, Title 40, Part 60, Appendix A-). The exempt compounds' content shall be determined by South Coast Air Quality Management District (SCAQMD) Laboratory Test Method 303 (Determination of Exempt Compounds) contained in the SCAQMD "Laboratory Methods of Analysis for Enforcement Samples" manual; or,
- (B) SCAQMD Method 304 [Determination of Volatile Organic Compounds (VOCs) in Various Materials] contained in the SCAQMD "Laboratory Methods of Analysis for Enforcement Samples" manual; ~~or,~~
- (C) SCAQMD Method 313 [Determination of Volatile Organic Compounds VOC by Gas Chromatography-Mass Spectrometry] in the SCAQMD's "Laboratory Methods of Analysis for Enforcement Samples" manual.
- ~~(BD)~~ VOC content determined to exceed the limits established by this rule through the use of any of the above-referenced test methods shall constitute a violation of this rule.

~~(CE)~~ Exempt Perfluorocarbon Compounds

The following classes of compounds:

- cyclic, branched, or linear, completely fluorinated alkanes;
- cyclic, branched, or linear, completely fluorinated ethers with no unsaturations;
- cyclic, branched, or linear, completely fluorinated tertiary amines with no unsaturations; and
- sulfur-containing perfluorocarbons with no unsaturations and with sulfur bonds only to carbon and fluorine,

~~will~~ shall be analyzed as exempt compounds for compliance with subdivision (~~e~~), only ~~when~~ at such time as manufacturers specify which individual compounds are used in the ~~coating~~ formulation of the coatings subject to this rule. In addition, the manufacturers shall also identify the test methods approved by the U.S. EPA, California Air Resources Board (CARB), and the SCAQMD ~~approved test methods~~ prior to any such analysis shall be used to quantify the amount of each exempt compound.

(2) Determination of ~~Metal Content~~ Iridescent Particles in Metallic/Iridescent Coatings

The metal and silicon content in metallic/iridescent coatings subject to the provisions of this rule shall be determined by the SCAQMD Method 311 (~~Determination~~ Analysis of Percent Metal in Metallic Coatings by Spectrographic Method) contained in the SCAQMD "Laboratory Methods of Analysis for Enforcement Samples" manual.

(3) Determination of Acid Content in Marine and Pleasure Craft Coatings

The acid content of any coating subject to the provisions of this rule shall be determined by ASTM D-1613-~~85-06~~ (2012) (Standard Test Method for Acidity in Volatile Solvents and Chemical Intermediates Used in Paint-, Varnish, Lacquer, and Related Products) ~~contained in the SCAQMD "Laboratory Methods of Analysis for Enforcement Samples" manual~~.

(4) Transfer Efficiency

The transfer efficiency of alternative marine coating and pleasure craft coating application methods, as defined by clause (d)(9)(A)(v), shall be determined in accordance with the SCAQMD method "Spray Equipment Transfer Efficiency Test Procedure for Equipment User, May 24, 1989," and SCAQMD "Guidelines for Demonstrating Equivalency With SCAQMD Approved Transfer Efficiency Spray Gun September 26, 2002."

(45) Determination of Efficiency of Emission Control System

(A) The efficiency of the collection device of the emission control system as specified in paragraph ~~(e)(2)(d)(5)~~ shall be determined by the ~~USEPA methods specified cited in 55 Federal Register 26865 (June 29, 1990), or any other method approved by the~~

~~USEPA, the California Air Resources Board, and the SCAQMD~~ below.:

- (i) U.S. EPA method cited in 55 Federal Register (FR) 26865, June 29, 1990; or
- (ii) SCAQMD's "Protocol for Determination of Volatile Organic Compounds (VOC) Capture Efficiency"; or
- (iii) Any other method approved by the U.S. EPA, CARB, and the SCAQMD Executive Officer.

(B) The efficiency of the control device of the emission control system as specified in paragraph (e)(25) and the VOC content in the control device exhaust gases, measured and calculated as carbon, shall be determined by U.S. EPA Test Methods 25, 25A, or SCAQMD Method 25.1 (Determination of Total Gaseous Non-Methane Organic Emissions as Carbon) as applicable. U.S. EPA Test Method 18, or CARB Method 422 shall be used to determine emissions of exempt compounds.

(56) Multiple Test Methods

When more than one test method or set of test methods are specified for any testing, a violation of any requirement of this rule established by any one of the specified test methods or set of test methods shall constitute a violation of the rule.

(67) All test methods referenced in this section shall be the most recently approved version.

(hi) Rule 442 Applicability

Any ~~marine coating operation~~ Marine Coating Operation or Pleasure Craft Coating Operation or any facility which is exempt pursuant to subdivision (j) from all or a portion of the VOC limits of subdivision (d) this rule shall comply with the provisions of Rule 442 - Usage of Solvents.

(ij) Exemptions

The provisions of this rule shall not apply to:

- (1) ~~marine~~ Marine coatings applied to interior surfaces of potable water containers.
- (2) ~~touch~~ Touch-up coatings, as defined by paragraph (c)(40) of this rule.
- (3) ~~marine coatings purchased before January 1, 1992, in containers of one quart or less and applied to pleasure craft.~~

- ~~(4) — antifoulant coatings applied to aluminum hulls.~~
- (~~5~~3) Any aerosol coating products.